

## Primer Sealer Undercoat



### Storage

The product must be stored in accordance to the national regulations. The product should be kept in a well-ventilated place, protected from heat and direct sunlight. The containers must be kept tightly closed.

### Handling

Handle with care. Stir well before use.

### Packing

3.64 Ltr  
14.56 Ltr

### Health and Safety

While applying paint, wear appropriate eye protection. In case of eye contact with product, rinse with plenty of water for at least 15 minutes. Keep away from ignition sources because it is flammable. The container should be protected from extreme hot and cold temperature. Remove as much paints as possible from brushes and rollers before cleaning. Don't breathe spray mist or dust. Ensure proper ventilation when applying paint. When empty, don't use its container for edible storage. Place out of reach of the children. In case of any emergency, undergo medical supervision as soon as possible. It should be properly closed and kept in an upright position after use.

## Description

Promax Water Based Primer is specially formulated to lock pores and imperfections of new & previously painted interior and exterior surfaces of wood, concrete, brickwork/ plaster and gypsum. It penetrates the porous surface, seals the porosity of the surface and as a result topcoat gives better coverage.

## Primer Sealer Undercoat

Promax Undercoat Sealer is formulated with special grade pigment, that provides extra whiteness with excellent opacity. It is a water-based primer for exterior walls and a suitable undercoat for exterior emulsions. It gives a tough film and as a result, it helps to provide a longer life of the total paint system.

## Product Information

Colours	White
Vehicle Type	Water-based
Solids (Vol %)*	42 ± 2
No of coats	2
Specific Gravity	1.40-1.50
Stability of thinned paint	To be used within 6-8 hours

## Recommended Use

Promax Undercoat Sealer can be used on the exterior as well as interior surfaces of bare wood, hardboard, plaster, brickwork, ceilings and cement etc. It can also be used to seal the poor distemper & lime wash the coated surface.

## Film Thickness and Spreading Rate

Dry film thickness	25-30 microns □
Theoretical Spreading Rate	10-12(m <sup>2</sup> /l)

## Application Data

Application Method	Spray	Brush	Roller
Thinner/Cleaner	Clean Water		
Thinning	50-70%		

## Drying Time

Temperature	Dry to touch	Dry to handle	Recoating Time
25 °C	30 Minutes	2 hours	3 hours
35 °C	15 Minutes	1 hours	2 hours

## Typical Paint System

Promax Primer Sealer Undercoat	1-2 Coat
Promax Excellent Wall Filling	1- 2 Coat
Promax Emulsion Topcoat	2- 3 Coat

