

Silicone Weathershield



Storage

The product must be stored in accordance to the national regulations. The product should be kept in a well-ventilated place, protected from heat and direct sunlight. The containers must be kept tightly closed.

Handling

Handle with care. Stir well before use.

Packing

0.91 Ltr
3.64 Ltr
14.56 Ltr

Health and Safety

While applying paint, wear appropriate eye protection. In case of eye contact with product, rinse with plenty of water for at least 15 minutes. Keep away from ignition sources because it is flammable. The container should be protected from extreme hot and cold temperature. Remove as much paints as possible from brushes and rollers before cleaning. Don't breathe spray mist or dust. Ensure proper ventilation when applying paint. When empty, don't use its container for edible storage. Place out of reach of the children. In case of any emergency, undergo medical supervision as soon as possible. It should be properly closed and kept in an upright position after use.

Description

Promax Silicone Weathershield Is one of the silicone-based product, specifically designed to provide best defense against extreme weather conditions. It has unique breathable paint technology that eradicates the water trapped in the walls.

Silicone Based Technology

Unique silicone technology allows paint film to stretch up-to 2x more than standard exterior wall paint, covers and prevents resurfacing of hairline cracks so that rain and moisture cannot seep in and damage the wall.

Product Information

Colours	Standard Colour Range
Vehicle Type	Silicone
Solids (Vol %)*	45 ± 2
No of coats	2-3 Coats
Specific Gravity	1.40-1.60
Stability of thinned paint	To be used within 6-8 hours

Recommended Use

Specially recommended for the exterior walls including plaster, concrete, gypsum, brickwork and exterior surfaces where long-lasting and washable finish is required.

Film Thickness and Spreading Rate

Dry film thickness	27-30 microns μ
Theoretical Spreading Rate	14-16(m ² /l)

Application Data

Application Method	Spray	Brush	Roller
Thinner/Cleaner	Clean Water		
Thinning	50-70%		

Drying Time

Temperature	Dry to touch	Dry to handle	Recoating Time
25 °C	30 Minutes	2 hours	3 hours
35 °C	15 Minutes	1 hours	2 hours

Typical Paint System

Promax Primer Sealer Undercoat	1-2 Coat
Promax Silicone Weathershield	2- 3 Coat

